

材料特性
MATERIAL CHARACTERISTICS

材 质	初始磁导率 μ_{iac}	相对损耗因子 $\tan \delta / \mu_{iac}$		比温度系数 $\alpha_{\mu \gamma}$	饱和磁束密度 B_{ms}	居里温度 T_c	电阻率 ρ	密度 d
Material	Initial permeability μ_{iac}	Relative loss factor		Relative temperature factor of μ_i 20to 60℃	Flux density (mT)	Curie temperature (℃)	Electric resistivity (Ω.m)	Density (g/cm³)
		(x10 ⁻⁶)	(MHz)					
NQ20	30	130	0.1	38~41	370	300	10 ⁶	5.1

