

材料特性

MATERIAL CHARACTERISTICS

材 质	初始磁导率 μ_{iac}	相对损耗因子 $\tan \delta / \mu_{iac}$		比温度系数 $\alpha_{\mu \gamma}$	饱和磁束密度 B_{ms}	居里温度 T_c	电阻率 ρ	密度 d
Material	Initial permeability μ_{iac}	Relative loss factor		Relative temperature factor of μ_i	Flux density	Curie temperature	Electric resistivity	Density
		($\times 10^{-6}$)	(MHz)	20to 60℃	(mT)	(℃)	($\Omega.m$)	(g/cm ³)
NB48H	300	25	0. 1	15~25	480	300	10^6	5.2

