

材料特性
MATERIAL CHARACTERISTICS

材 质	初始磁导率 μ_{iac}	相对损耗因子 $\tan \delta / \mu_{iac}$		比温度系数 $\alpha \mu \gamma$	饱和磁束密度 B_{ms}	居里温度 T_c	电阻率 ρ	密度 d
Material	Initial permeability μ_{iac}	Relative loss factor		Relative temperature factor of μ_i 20to 60℃	Flux density (mT)	Curie temperature (℃)	Electric resistivity ($\Omega.m$)	Density (g/cm ³)
		($\times 10^{-6}$)	(MHz)					
NB45H	350	25	0.1	7~22	450	250	10^6	5.2

